

AMENDMENTS TO THE CLAIMS

1-52. (Cancelled)

53. (Previously presented) A method for solid-state friction stirring of a surface of a high melting temperature material, said method comprising the steps of:

- (1) providing a friction stirring tool having a friction stirring surface;
- (2) disposing a superabrasive material on the friction stirring surface; and
- (3) friction stirring the surface of the high melting temperature material using a solid-state process wherein the high melting temperature material substantially avoids a liquid state.

54. (Previously presented) The method as defined in claim 53 wherein the method further comprises the step of allowing the high melting temperature material to at least partially experience a liquid phase.

55. (Previously presented) The method as defined in claim 53 wherein the method further comprises the step of selecting the high melting temperature material from the group of high melting

temperature materials including ferrous alloys, non-ferrous materials, superalloys, titanium, cobalt alloys typically used for hard-facing, and air hardened or high speed steels.

56. (Previously presented) The tool as defined in claim 53 wherein the tool further comprises the superabrasive being selected from the group of materials comprised of compounds including elements extending from IIIA, IVA, VA, VIA, IIIB, IVB, and VB on the periodic table of the elements.

57. (Previously presented) The method as defined in claim 53 wherein the method further comprises the step of also friction stirring below the surface of the high melting temperature material to perform solid-state processing of the high melting temperature material.

58. (Previously presented) The method as defined in claim 53 wherein the method further comprises the step of forming the friction stirring surface as a pin on the friction stirring tool.

59. (Previously presented) The method as defined in claim 53 wherein the method further comprises the step of making the friction stirring surface as a shoulder without a pin on the friction stirring tool.

60. (Previously presented) The method as defined in claim 53

wherein the method further comprises the step of making the friction stirring tool from a pin and shoulder combination, wherein only the pin makes contact with the high melting temperature surface when surface friction stirring, and wherein the pin and the shoulder make contact with the high melting temperature surface when friction stirring below the surface.

61. (Previously presented) The method as defined in claim 53

wherein the method further comprises the step of friction stir processing the high melting temperature material to thereby alter the characteristics of the high melting temperature material through substantially solid-state processing.

62. (Previously presented) The method as defined in claim 53

wherein the method further comprises the step of friction stir processing the high melting temperature material to thereby alter the characteristics of the high melting temperature material through partial liquid phase processing.

63. (Previously presented) The method as defined in claim 53

wherein the method further comprises the step of friction stir mixing a second material into the high melting temperature material to thereby alter the characteristics of the high melting

temperature material through substantially solid-state processing of the high melting temperature material and the second material.

64. (Previously presented) The method as defined in claim 53 wherein the method further comprises the step of friction stir mixing a second material into the high melting temperature material to thereby alter the characteristics of the high melting temperature material through at least partially liquid phase processing of the high melting temperature material and the second material.

65. (Previously presented) The method as defined in claim 60 wherein the method further comprises the step of forming the pin as a cylindrical shape, wherein the pin is concentric with and parallel to a lengthwise axis of the shoulder from which it extends outwardly.

66. (Previously presented) The method as defined in claim 65 wherein the method further comprises the step of forming the shoulder as an annular shape having an outer rim that extends outwardly above a central point.

67. (Previously presented) A method for friction stir processing a surface of a high melting temperature material, said method comprising the steps of:

- (1) providing a friction stir processing tool having a friction stir processing surface;
- (2) disposing a superabrasive material on the friction stir processing surface; and
- (3) friction stir processing the surface of the high melting temperature material to thereby alter the characteristics of the high melting temperature material through substantially solid-state processing of the high melting temperature material.

68. (Previously presented) The method as defined in claim 67 wherein the method further comprises the step of selecting the high melting temperature material from the group of high melting temperature materials including ferrous alloys, non-ferrous materials, superalloys, titanium, cobalt alloys typically used for hard-facing, and air hardened or high speed steels.

69. (Previously presented) The method as defined in claim 67 wherein the method further comprises the step of also friction stir processing below the surface of the high melting temperature material.

70. (Previously presented) The method as defined in claim 67 wherein the method further comprises the step of forming the friction stir processing surface as a pin on the friction stir processing tool.

71. (Previously presented) The method as defined in claim 67

wherein the method further comprises the step of making the friction stir processing surface as a shoulder without a pin on the friction stir processing tool.

72. (Previously presented) The method as defined in claim 67

wherein the method further comprises the step of making the friction stir processing tool from a pin and shoulder combination, wherein only the pin makes contact with the high melting temperature surface when surface friction stir processing, and wherein the pin and the shoulder make contact with the high melting temperature surface when friction stir processing below the surface.

73. (Previously presented) The method as defined in claim 67

wherein the method further comprises the step of friction stir mixing a second material into the high melting temperature material to thereby alter the characteristics of the high melting temperature material through substantially solid-state processing of the high melting temperature material and the second material.

74. (Previously presented) The method as defined in claim 67

wherein the method further comprises the step of friction stir mixing a second material into the high melting temperature material to thereby alter the characteristics of the high melting

temperature material through at least partial liquid phase processing of the high melting temperature material and the second material.

75. (Previously presented) The method as defined in claim 72 wherein the method further comprises the step of forming the pin as a cylindrical shape, wherein the pin is concentric with and parallel to a lengthwise axis of the shoulder from which it extends outwardly.

76. (Previously presented) The method as defined in claim 75 wherein the method further comprises the step of forming the shoulder as an annular shape having an outer rim that extends outwardly above a central point.

77. (Previously presented) A method for friction stir mixing a surface of a high melting temperature material through substantially solid-state processing, said method comprising the steps of:

(1) providing a friction stir mixing tool having a friction stir mixing surface;

(2) disposing a superabrasive material on the friction stir mixing surface; and

(3) friction stir mixing a second material into the surface of the high melting temperature material to thereby alter the characteristics of the high melting temperature material through substantially solid-state processing of the high melting temperature material and the second material.

78. (Previously presented) The method as defined in claim 77 wherein the method further comprises the step of selecting the high melting temperature material from the group of high melting temperature materials including ferrous alloys, non-ferrous materials, superalloys, titanium, cobalt alloys typically used for hard-facing, and air hardened or high speed steels.

79. (Previously presented) The method as defined in claim 77 wherein the method further comprises the step of also friction stir mixing below the surface of the high melting temperature material.

80. (Previously presented) The method as defined in claim 77 wherein the method further comprises the step of forming the friction stir mixing surface as a pin on the friction stir mixing tool.

81. (Previously presented) The method as defined in claim 77 wherein the method further comprises the step of making the

friction stir mixing surface as a shoulder without a pin on the friction stir mixing tool.

82. (Previously presented) The method as defined in claim 77 wherein the method further comprises the step of making the friction stir mixing tool from a pin and shoulder combination, wherein only the pin makes contact with the high melting temperature surface when surface friction stir mixing, and wherein the pin and the shoulder make contact with the high melting temperature surface when friction stir mixing below the surface.

83. (Previously presented) The method as defined in claim 82 wherein the method further comprises the step of forming the pin as a cylindrical shape, wherein the pin is concentric with and parallel to a lengthwise axis of the shoulder from which it extends outwardly.

84. (Previously presented) The method as defined in claim 83 wherein the method further comprises the step of forming the shoulder as an annular shape having an outer rim that extends outwardly above a central point.

85-99. (Withdrawn)

100. (Previously presented) A method for joining a first high melting temperature material to a second high melting temperature material through substantially solid-state processing, said method comprising the steps of:

(1) providing a friction stirring tool having a friction stirring surface;

(2) disposing a superabrasive material on the friction stirring surface; and

(3) friction stirring the first high melting temperature material to the second high melting temperature material, wherein the first high melting temperature material and the second high melting temperature material are functionally friction stirred together using a substantially solid-state process.

101. (Previously presented) The method as defined in claim 100 wherein the method further comprises the step of selecting the first and the second high melting temperature materials from the group of high melting temperature materials including ferrous alloys, non-ferrous materials, superalloys, titanium, cobalt alloys typically used for hard-facing, and air hardened or high speed steels.

102. (Previously presented) The method as defined in claim 101 wherein the method further comprises the step of friction stir welding the first high melting temperature material to the second

high melting temperature material using the substantially solid-state process.

103. (Previously presented) The method as defined in claim 102 wherein the method further comprises the step of friction stir processing the first high melting temperature material and the second high melting temperature material using the substantially solid-state process.

104. (Previously presented) The method as defined in claim 103 wherein the method further comprises the step of friction stir mixing a second material with the first high melting temperature material and the second high melting temperature material using the substantially solid-state process.